

Characteristics of *Filtraflo 411* For the Paint Industry

G E Brightness		78-82
Refractive Index		1,49
Hegman Grind Gauge Reading	(1)	0
Gloss 60°	(2)	12,7
Gloss 85°	(2)	8,5
Gardner Coleman Oil Absorption		180%
ASTM Rub-Out Oil Absorption		150%
Water Absorption		250%
Surface Area in m ² /g	(3)	2,6

Remarks

- (1) Using an alkyd high gloss enamel paint containing 29% by weight of binder solids.
- (2) Using same paint as in (1). This paint gives a gloss of 88,7 and a sheen of 99,6. The dosages were 6g and 12g/150g paint.
- (3) Using Blaine Air Permeability Method - A S T M C - 204.